ANA
LABORATORIES
130-B, HARDING AVE. BELLMAWR, NJ 08031
P.O. BOX 727 BELLMAWR, NJ 08099-0029
PHONE: 1-800-648-2625 or 856-931-0011
FAX: 856-931-5205
EMAIL: lab@analaboratories.com

Lab Number:	**S09M18457**
Customer I.D:	**AMTRAKTX**
Source:	**500 BASELINE**
Sample Date:	**12/22/2009**
Product Type:	**B-100**
Report Date:	**12/31/2009**

AMTRAK
ATTENTION:
TIM COOPER
400 SOUTH HOUSTON ST. STE. 100
DALLAS, TX 75202

TEST	DESCRIPTION	ASTM	SPECIFICATION	RESULT	UNITS
1)	Flash Point	D-93	**130 minimum**	**165**	degrees Celsius
2)	Water and Sediment	D-2709	**0.0500 maximum**	**0.0150**	volume %
3)	Kinematic Viscosity @ 40 C	D-445	**1.9 - 6.0**	**4.62**	cSt
4)	Sulfated Ash	D-874	**0.020 maximum**	**0.001**	weight %
5)	Sulfur	D-5453	**15 maximum**	**0.0005**	parts per million
6)	Copper Strip Corrosion	D-130	**No. 3 maximum**	**1a**	rating
7)	Cetane Index	D-976	**47 minimum**	**60.3**	
8)	Cloud Point	D-2500	**Report**	**17**	degrees Celsius
9)	Carbon Residue	D-4530	**0.0050 maximum**	**0.0031**	weight %
11)	Acid Number	D-664	**0.50 maximum**	**0.30**	mg KOH/g
12)	Free Glycerin	D-6584	**0.020 maximum**	**0.230 ****	volume %
13)	Total Glycerin	D-6584	**0.240 maximum**	**0.250 ****	volume %
14)	Phosphorus	D-4951	**0.0010 maximum**	**<0.0001**	weight %
14)	Distillation Temperature 90%	D-1160	**360 maximum**	**341**	degrees Celsius
15)	Calcium and Magnesium	EN14538	**5 maximum**	**<1**	parts per million
16)	Sodium and Potassium	EN14538	**5 maximum**	**<1**	parts per million
17)	Oxidation Stability	EN14112	**3 minimum**	**>10**	hours

Comment: Results for Free and Total Glycerin are not with ASTM specifications.

For ANA LABORATORIES, INC.

ANA
LABORATORIES
130-B, HARDING AVE. BELLMAWR, NJ 08031
P.O. BOX 727 BELLMAWR, NJ 08099-0029
PHONE: 1-800-648-2625 or 856-931-0011
FAX: 856-931-5205
EMAIL: lab@analaboratories.com

Lab Number:	**S10B2442**
Customer I.D:	**AMTRAKTX**
Source:	**500 B100**
Sample Date:	**1/21/2010**
Product Type:	**B-100**
Report Date:	**2/12/2010**

AMTRAK
ATTENTION:
TIM COOPER
400 SOUTH HOUSTON ST. STE. 100
DALLAS, TX 75202

TEST	DESCRIPTION	ASTM	SPECIFICATION	RESULT	UNITS
1)	Flash Point	D-93	**130 minimum**	**146**	degrees Celsius
2)	Water and Sediment	D-2709	**0.0500 maximum**	**0.0100**	volume %
3)	Kinematic Viscosity @ 40 C	D-445	**1.9 - 6.0**	**4.67**	cSt
4)	Sulfated Ash	D-874	**0.020 maximum**	**0.001**	weight %
5)	Sulfur	D-5453	**15 maximum**	**0.0007**	parts per million
6)	Copper Strip Corrosion	D-130	**No. 3 maximum**	**1a**	rating
7)	Cetane Index	D-976	**47 minimum**	**59.1**	
8)	Cloud Point	D-2500	**Report**	**17**	degrees Celsius
9)	Carbon Residue	D-4530	**0.0050 maximum**	**0.049**	weight %
11)	Acid Number	D-664	**0.50 maximum**	**0.28**	mg KOH/g
12)	Free Glycerin	D-6584	**0.020 maximum**	**0.00**	volume %
13)	Total Glycerin	D-6584	**0.240 maximum**	**0.00**	volume %
14)	Phosphorus	D-4951	**0.0010 maximum**	**<0.0001**	weight %
14)	Distillation Temperature 90%	D-1160	**360 maximum**	**331**	degrees Celsius
15)	Calcium and Magnesium	EN14538	**5 maximum**	**<1**	parts per million
16)	Sodium and Potassium	EN14538	**5 maximum**	**<1**	parts per million
17)	Oxidation Stability	EN14112	**3 minimum**	**>10**	hours

Comment: Results are within specifications.

For ANA LABORATORIES, INC.

ANA
LABORATORIES
130-B, HARDING AVE. BELLMAWR, NJ 08031
P.O. BOX 727 BELLMAWR, NJ 08099-0029
PHONE: 1-800-648-2625 or 856-931-0011
FAX: 856-931-5205
EMAIL: lab@analaboratories.com

Lab Number:	**S10B9637**
Customer I.D:	**AMTRAKTX**
Source:	**Fort Worth B-100**
Sample Date:	**2/9/2010**
Product Type:	**B-100**
Report Date:	**2/22/2010**

AMTRAK
ATTENTION:
TIM COOPER
400 SOUTH HOUSTON ST. STE. 100
DALLAS, TX 75202

TEST	DESCRIPTION	ASTM	SPECIFICATION	RESULT	UNITS
1)	Flash Point	D-93	**130 minimum**	**163**	degrees Celsius
2)	Water and Sediment	D-2709	**0.0500 maximum**	**0.0100**	volume %
3)	Kinematic Viscosity @ 40 C	D-445	**1.9 - 6.0**	**4.69**	cSt
4)	Sulfated Ash	D-874	**0.020 maximum**	**0.001**	weight %
5)	Sulfur	D-5453	**15 maximum**	**0.0007**	parts per million
6)	Copper Strip Corrosion	D-130	**No. 3 maximum**	**1a**	rating
7)	Cetane Index	D-976	**47 minimum**	**58.9**	
8)	Cloud Point	D-2500	**Report**	**17**	degrees Celsius
9)	Carbon Residue	D-4530	**0.0050 maximum**	**0.022**	weight %
11)	Acid Number	D-664	**0.50 maximum**	**0.28**	mg KOH/g
12)	Free Glycerin	D-6584	**0.020 maximum**	**0.095****	volume %
13)	Total Glycerin	D-6584	**0.240 maximum**	**0.101**	volume %
14)	Phosphorus	D-4951	**0.0010 maximum**	**<0.0001**	weight %
14)	Distillation Temperature 90%	D-1160	**360 maximum**	**338**	degrees Celsius
15)	Calcium and Magnesium	EN14538	**5 maximum**	**<1**	parts per million
16)	Sodium and Potassium	EN14538	**5 maximum**	**<1**	parts per million
17)	Oxidation Stability	EN14112	**3 minimum**	**>10**	hours

Comment: **Test result is not within specifications.

For ANA LABORATORIES, INC.

ANA LABORATORIES
130-B, HARDING AVE. BELLMAWR, NJ 08031
P.O. BOX 727 BELLMAWR, NJ 08099-0029
PHONE: 1-800-648-2625 or 856-931-0011
FAX: 856-931-5205
EMAIL: lab@analaboratories.com

Lab Number:	**S10L4238**
Customer I.D:	**AMTRAKTX**
Source:	**Fort Worth B-100**
Sample Date:	**10/27/2010**
Product Type:	**B-100**
Report Date:	**11/11/2010**

AMTRAK
ATTENTION:
TIM COOPER
400 SOUTH HOUSTON ST. STE. 100
DALLAS, TX 75202

TEST	DESCRIPTION	ASTM	SPECIFICATION	RESULT	UNITS
1)	Flash Point	D-93	**130 minimum**	**179**	degrees Celsius
2)	Water and Sediment	D-2709	**0.0500 maximum**	**0.0100**	volume %
3)	Kinematic Viscosity @ 40 C	D-445	**1.9 - 6.0**	**4.76**	cSt
4)	Sulfated Ash	D-874	**0.020 maximum**	**0.001**	weight %
5)	Sulfur	D-5453	**15 maximum**	**0.0014**	parts per million
6)	Copper Strip Corrosion	D-130	**No. 3 maximum**	**1a**	rating
7)	Cetane Index	D-976	**47 minimum**	**59.6**	
8)	Cloud Point	D-2500	**Report**	**16**	degrees Celsius
9)	Carbon Residue	D-4530	**0.0050 maximum**	**0.029**	weight %
11)	Acid Number	D-664	**0.50 maximum**	**0.3**	mg KOH/g
12)	Free Glycerin	D-6584	**0.020 maximum**	**0.0**	volume %
13)	Total Glycerin	D-6584	**0.240 maximum**	**0.0**	volume %
14)	Phosphorus	D-4951	**0.0010 maximum**	**<0.0001**	weight %
14)	Distillation Temperature 90%	D-1160	**360 maximum**	**336**	degrees Celsius
15)	Calcium and Magnesium	EN14538	**5 maximum**	**<1**	parts per million
16)	Sodium and Potassium	EN14538	**5 maximum**	**<1**	parts per million
17)	Oxidation Stability	EN14112	**3 minimum**	**>10**	hours

Comment: Test data as per your request.

For ANA LABORATORIES, INC.